

Treated with Heraeus long life technology

Conventional coating

200 nm


Quartz

Longlife Technology Doubles the Efficiency of High Power Amalgam Lamps

Lifetime dependency of coating

UVC radiation has an intense bactericidal action. Microorganisms such as viruses, bacteria, yeasts and spores are effectively inactivated without the addition of chemicals. The energy of UVC radiation is sufficient to break down chemical compounds or to achieve molecular restructuring. In addition, oxidation processes and decomposition reactions of organic compounds are initiated.

Amalgam UVC lamps with Longlife Technology offer a disinfection action which is virtually constant over the lamp operating life. While the UVC output of uncoated lamps drops by around 50% after 8,000 hours, the Amalgam UVC lamps with Longlife Technology have a reduction in UVC output of approximately 10% at up to 16,000 hours.




Influence on quartz transmission

Because of the higher UVC output at end of lamp life due to minimal absorption and the extended operating life, Heraeus Longlife Amalgam lamps offer disinfection systems a significant potential for savings. The benefits are fewer lamps and system consumables, less energy consumption and maintenance costs.

Compared with standard low pressure mercury lamps, the amalgam lamps offer the extremely good UVC efficiency, which is typical of mercury low pressure lamps, but with a significantly higher UVC output.

With Longlife Technology, lamps can be produced which have no discoloration and even after 16,000 hours still provide a UVC output greater than 90 % of the original output.

Transmission of coatings



Technical data of compared lamps

Heraeus Amalgam lamps offer great potential for savings in number of lamps, system components, energy consumption and service intervals – while significantly reducing the operating costs of disinfection systems.

The comparison below shows an example of different lamp types and their consumption over six years. Based on the same demand for UVC output, different numbers of lamps per system are needed.

Lamp type	Lamps/system	Quantity of lamps	Initial UVC efficiency	UVC efficiency @ end of life									
Heraeus Longlife Amalgam Lamp	5	15 lamps in 48,000 h	35 %	32 %									
Operation hours													
	0 h	4,000 h	8,000 h	12,000 h	16,000 h	20,000 h	24,000 h	28,000 h	32,000 h	36,000 h	40,000 h	44,000 h	48,000 h
Lamp change													
Amalgam Lamp with conventional coating	6	24 lamps in 48,000 h	31 %	24 %									
Operation hours													
	0 h	4,000 h	8,000 h	12,000 h	16,000 h	20,000 h	24,000 h	28,000 h	32,000 h	36,000 h	40,000 h	44,000 h	48,000 h
Lamp change													
Conventional Amalgam Lamp	10	60 lamps in 48,000 h	35 %	18 %									
Operation hours													
	0 h	4,000 h	8,000 h	12,000 h	16,000 h	20,000 h	24,000 h	28,000 h	32,000 h	36,000 h	40,000 h	44,000 h	48,000 h
Lamp change													

www.heraeus-noblelight.com

Germany
Heraeus Noblelight GmbH
 Heraeusstraße 12-14
 63450 Hanau
 Phone +49 6181 35-5964
 Telefax +49 6181 35-9926
 hng-uv@heraeus.com

Great Britain
Heraeus Amba Ltd.
 Thorpe Way
 Banbury OX16 4ST
 Phone +44 1295 272666
 Telefax +44 1295 272611
 ambalamps@heraeusamba.co.uk

USA
Heraeus Noblelight Fusion UV Inc.
 910 Clopper Road
 Gaithersburg, Maryland
 Gaithersburg, Maryland
 Phone + 1 301 527 2260
 Telefax + 1 301 527 2661
 info.hnfn@noblelight.com

China
Heraeus Noblelight (Shenyang). Ltd.
 5F, 16th Building
 No.99 TianZhou Rd.
 200233 Shanghai
 Phone +86 21 54263900-258
 Telefax +86 21 54263911
 info.hns@heraeus.com



Wissenschaftliche Apparaturen
 und Industrieanlagen AG
 Bruggacherstrasse 24
 CH-8117 Fällanden

Tel. 044 317 57 57
 Fax 044 317 57 77
<http://www.wisag.ch>
 e-mail: info@wisag.ch